

(19)

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 211 050 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
05.06.2002 Bulletin 2002/23

(51) Int Cl.7: **B29C 47/32, B29C 47/50,**
B29C 47/92
// B29L30:00

(21) Application number: 01309802.5

(22) Date of filing: 21.11.2001

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR
Designated Extension States:
AL LT LV MK RO SI

(72) Inventors:
• **Ogawa, Y.,**
c/o Bridgestone Corp. Technical Center
Kodaira City, Tokyo (JP)
• **Iizuka, S.,**
c/o Bridgestone Corp. Technical Center
Kodaira City, Tokyo (JP)

(30) Priority: 22.11.2000 JP 2000355402

(71) Applicant: **BRIDGESTONE CORPORATION**
Tokyo 104-0031 (JP)


(74) Representative: **Whalley, Kevin**
MARKS & CLERK,
57-60 Lincoln's Inn Fields
London WC2A 3LS (GB)

(54) Method for extruding tire rubber material

(57) Tire rubber material is highly accurately and efficiently extruded by a positive displacement extruding system (1) that includes, as seen from an upstream side of the tire rubber, a screw extruder unit (2), a gear pump unit (3) and an extrusion head unit (4) with an extrusion nozzle (5), which are connected in series with each other. While the tire rubber is caused to flow through the

extruding system (1), the temperature of the rubber material is measured and controlled to be within a predetermined temperature range, in accordance with the measured temperature of the rubber material. The rubber material maintained at a controlled temperature is extruded from the extrusion nozzle (5), thereby improving the positive displacement performance of the extruding system.

FIG. 1



Description

[0001] The present invention relates to a method for extruding tire rubber material to be applied onto the outer peripheral surface of a rotatable support for successively forming a green tire thereon in a highly accurate and efficient manner.

[0002] Pneumatic tires comprise reinforcing members such as rubberized cords, and various rubber members. Therefore, prior to vulcanization of tires, it is necessary to form a green tire by laying reinforcing materials such as unvulcanized rubber materials and unvulcanized rubberized cord materials.

[0003] Recently, properties required for tires tend to be highly sophisticated and more diversified, with a resultant diversification of tire-constructional members and complication of tire shaping steps. Therefore, it is difficult to completely automate the shaping step and manual works are still required in many instances, making it difficult to significantly improve the tire shaping efficiency and laying accuracy of various materials. Particularly, since the laying accuracy is highly influential over the quality of tires, it is strongly demanded to improve the laying accuracy together with the increase of the shaping efficiency.

[0004] In order to satisfy such demands, JP-B-7-94155 discloses a technology wherein an outlet orifice of a positive displacement extruder is located adjacent to a position for feeding a rubber material onto a rotatable support and the rubber material is directly extruded on the support through the outlet orifice.

[0005] With the technology disclosed in JP-B-7-94155, it is difficult to maintain the cross-sectional shape of a continuously extruded rubber material during the laying, due mainly to the so-called surging, i.e., fluctuation of the extrusion amount inherent to the extruder when the extruded rubber material has particularly a thin gauge. And also, the following problem is caused because various rubber materials are laid on the rotating support.

[0006] That is to say, since the viscoelastic characteristic differs in accordance with the kind of the rubber material, the die swell quantity tends to differ accordingly. Thus, it is required to take some measure for controlling the cross-sectional shape of the rubber material to be laid. This is attained by replacing the die with another die, or by making the die form variable. In any case, such measure for coping with the different die swell quantities requires time-consuming process, and often lowers the laying productivity.

[0007] To solve this problem, JP-A-8-21354 discloses a positive displacement pump having a rotary valve enabling to feed a highly viscous material such as tire rubber material at a constant flow rate without deteriorating the volumetric precision, and facilitating the flow of material, and proposes that the tire rubber materials discharged from the positive displacement pump is fed on to a rotatable supporter.

[0008] However, the positive displacement pump disclosed in JP-A-8-21354 has a complicated structure, and is faced with limitation of the feeding amount depending on the types of rubber materials, thereby making it difficult to achieve the desired improvement in productivity.

[0009] In order to cope with these problems, JP-A-2000-79642 discloses a positive displacement extruding system that includes, as seen from an upstream side of the tire rubber, a screw extruder unit, a gear pump unit and an extrusion head unit with an extrusion nozzle, which are connected in series with each other. A pair of rollers is arranged adjacent to the extrusion orifice and also to a rotatable support, so as to form a roller die by a gap between the rollers. The rubber material discharged from the extrusion orifice to have a gauge that exceeds the gap is passed through the roller die, so as to stabilize the cross-sectional shape of the rubber material, and is then adhered onto the rotating supporter.

[0010] The positive displacement extruding system disclosed in JP-A-2000-79642 makes it readily possible to compensate for the various die-swelling amounts that may be caused upon replacing rubber materials, to simplify the structure of the entire system, and to prevent limitations on feeding amounts of any types of rubber materials, thereby allowing to ensure a higher productivity. However, in order to enhance the flow property of the rubber material within the system, a relatively long time is often required so as to warm-up the rubber material. Moreover, when the flow property of the rubber material within the system is still insufficient, the extrusion nozzle may exhibit insufficient discharging performance for directly feeding the rubber material onto the rotatable support. It is highly desirable to eliminate these problems and improve the positive displacement extruding system disclosed in JP-A-2000-79642.

[0011] Accordingly, it is a primary object of the present invention to provide a technology that improves the positive displacement extruding system disclosed in JP-A-2000-79642, in such a manner as to achieve a sufficient flow property of the rubber material within the system and a satisfactory discharging performance of the extrusion nozzle.

[0012] According to one aspect of the present invention, there is provided a method for extruding a tire rubber material by a positive displacement extruding system that includes, as seen from an upstream side of the tire rubber, a screw extruder unit, a gear pump unit and an extrusion head unit with an extrusion nozzle, which are connected in series with each other, said method comprising the steps of: measuring the temperature of the rubber material flowing through the extruding system; and controlling the rubber material to be within a predetermined temperature, in accordance with the measured temperature of the rubber material, while the tire rubber is caused to flow through the extruding system, and maintaining the predetermined temperature of the rubber material before it is extruded from the extru-

sion nozzle.

[0013] Advantageously, the rubber material flowing through the screw extruder unit and the gear pump unit is maintained at a temperature within a range of approximately 85-95°C, and the rubber material flowing through the extrusion head unit is maintained at a temperature within a range of approximately 95-100°C.

[0014] It is preferred that the screw extruder unit of the extruding system includes a cylinder and a screw that is rotatable in the cylinder, wherein the cylinder is controlled to have a temperature that is lower than the temperature of the rubber material flowing adjacent to a downstream end of the screw.

[0015] It is preferred that at least one of the screw extruder unit, gear pump unit and extrusion head unit of the extruding system is provided with a heater that is operated in accordance with the measured temperature of the rubber material, wherein the heater is operated before the extruding system is operated, so as to pre-heat the rubber material within the extruding system.

[0016] It is also preferred that at least one of the screw extruder unit, gear pump unit and extrusion head unit of the extruding system is provided with a pressure sensor for measuring the pressure of the rubber material flowing through the extruding system, wherein the screw extruder unit and/or gear pump unit is operated at a speed that is controlled in accordance with the pressure of the rubber material measured by the pressure sensor.

[0017] The extruding system may be charged with a rubber material at a temperature within a range of approximately 20-30°C, or with a rubber material at a temperature within a range of approximately 60-80°C.

[0018] According to another aspect of the present invention, there is provided a positive displacement extruding system for extruding a tire rubber material, including, as seen from an upstream side of the tire rubber, a screw extruder unit, a gear pump unit and an extrusion head unit with an extrusion nozzle, which are connected in series with each other, said system comprising: at least one temperature sensor provided for at least one of said screw extruder unit, said gear pump unit and said extrusion head unit, for measuring the temperature of the rubber material flowing through the extruding system; and control means for controlling the rubber material to be within a predetermined temperature, in accordance with the measured temperature of the rubber material, while the tire rubber is caused to flow through the extruding system, and maintaining the predetermined temperature of the rubber material before it is extruded from the extrusion nozzle.

[0019] Advantageously, the control means comprises at least one heater provided for at least one of the screw extruder unit, gear pump unit and extrusion head unit, wherein said at least one heater is operable in accordance with the measured temperature of the rubber material.

[0020] It is preferred that the positive displacement extruding system according to the present invention fur-

ther comprises at least one pressure sensor provided for at least one of the screw extruder unit, gear pump unit and extrusion head unit, for measuring the pressure of the rubber material flowing through the extruding system, wherein the screw extruder unit and/or gear pump unit is operable at a speed that is controlled in accordance with the pressure of the rubber material measured by the pressure sensor.

[0021] The present invention will be described below in further detail, with reference to the preferred embodiment shown in the accompanying drawings.

[0022] FIG. 1 is a side view of a positive displacement extruding apparatus for carrying out the method according to the present invention, in combination with a roller die that is arranged adjacent to a rotatable support.

[0023] FIG. 2 is a sectional view of the extruder body shown in FIG. 1, taken along a plane including the screw axis.

[0024] FIG. 3 is a rear view of a gear pump of the extruding apparatus shown in FIG. 1, as seen from the direction of arrow A.

[0025] FIGS. 4 and 5 are sectional views of the gear pump, taken along the lines IV-IV and V-V in FIG. 3, respectively.

[0026] FIG. 6 is a side view of the extrusion head of the extruding apparatus shown in FIG. 1.

[0027] Referring now to FIG. 1, there is shown an extruding system 1 for extruding an unvulcanized tire rubber material having a predetermined constant cross-section, with a predetermined constant volume. The extruding system 1 includes a screw extruder unit 2; a gear pump unit 3 coupled to the discharge end of the extruder unit 2, and an extrusion head unit 4 coupled to the discharge side of the gear pump unit 3 and including an extrusion nozzle 5. The extruding system 1 is of a positive displacement type, mainly by virtue of the gear pump unit 3. The extruding system 1 to which the present invention may be suitably applied is generally disclosed in the applicants' co-pending U.S. Patent Application No. 09/327,613, the disclosure of which is herein incorporated by reference.

[0028] As shown in FIG. 2, the screw extruder unit 2 includes a screw 10 that is rotatably supported in a cylinder 11. For measuring the temperature of the rubber material flowing through the interior of the cylinder 11, a temperature sensor 12 is provided at the downstream portion of the screw 10, which may be comprised of a thermistor. A heater 13 is arranged to surround the cylinder 11, for heating the rubber material flowing through the interior of the extruder unit 2. The heater 13 is preferably comprised of an electric hot wire.

[0029] As shown in FIGS. 3 to 5, the gear pump unit 3 includes a driving gear 14 and a driven gear 15, which are in mesh with each other and rotatable in opposite directions. For measuring the temperature of the rubber material flowing through the interior of the gear pump unit 3, a temperature sensor 16 is provided adjacent to at least one of the gears 14, 15, i.e., adjacent to the driv-

FIG. 2




FIG. 3




FIG. 4




FIG. 3




FIG. 5






FIG. 6





(19)

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 211 050 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
26.11.2003 Bulletin 2003/48

(51) Int Cl.7: **B29C 47/32, B29C 47/50,
B29C 47/92
// B29L30:00**

(43) Date of publication A2:
05.06.2002 Bulletin 2002/23

(21) Application number: **01309802.5**

(22) Date of filing: **21.11.2001**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI

(72) Inventors:
• **Ogawa, Y.,**
c/o Bridgestone Corp. Technical Center
Kodaira City, Tokyo (JP)
• **Iizuka, S.,**
c/o Bridgestone Corp. Technical Center
Kodaira City, Tokyo (JP)

(30) Priority: **22.11.2000 JP 2000355402**


(71) Applicant: **BRIDGESTONE CORPORATION**
Tokyo 104-0031 (JP)

(74) Representative: **Whalley, Kevin
MARKS & CLERK,**
57-60 Lincoln's Inn Fields
London WC2A 3LS (GB)

(54) Method for extruding tire rubber material

(57) Tire rubber material is highly accurately and efficiently extruded by a positive displacement extruding system (1) that includes, as seen from an upstream side of the tire rubber, a screw extruder unit (2), a gear pump unit (3) and an extrusion head unit (4) with an extrusion nozzle (5), which are connected in series with each other. While the tire rubber is caused to flow through the extruding system (1), the temperature of the rubber material is measured and controlled to be within a predetermined temperature range, in accordance with the measured temperature of the rubber material. The rubber material maintained at a controlled temperature is extruded from the extrusion nozzle (5), thereby improving the positive displacement performance of the extruding system.

FIG. 1



EP 1 211 050 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 30 9802

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	EP 0 492 425 A (BRIDGESTONE CORP) 1 July 1992 (1992-07-01) * column 4, line 2 * * column 15, paragraph 2; claim 13: figures 2,3 *	1,4-6, 9-11	B29C47/32 B29C47/50 B29C47/92 //B29L30:00
X	EP 0 508 080 A (TROESTER MASCHF PAUL) 14 October 1992 (1992-10-14) * column 6, last line - column 7, line 11; figure 5 *	1,6,9,11	
A	EP 0 968 814 A (BRIDGESTONE CORP) 5 January 2000 (2000-01-05) * claim 10; figure 1 *	1,9-11	
A	US 4 171 193 A (RAHLFS HERBERT K) 16 October 1979 (1979-10-16) * claims 1-10 *	11	
A	US 5 378 415 A (GOHLISCH HANS J ET AL) 3 January 1995 (1995-01-03) * claim 2 *	11	
A	WO 90 14939 A (BECK ERICH) 13 December 1990 (1990-12-13) * claim 1 *	1,9,11	TECHNICAL FIELDS SEARCHED (Int.Cl.7) B29D B29C
A	WO 89 03754 A (NILSSON BO) 5 May 1989 (1989-05-05) * the whole document *	9,11	
A	EP 0 391 003 A (KOBE STEEL LTD) 10 October 1990 (1990-10-10) * claim 1 *	1	
P,A	EP 1 084 814 A (TOYO TIRE & RUBBER CO) 21 March 2001 (2001-03-21) * claim 1; figure 1 *	1	
-/-			
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 8 October 2003	Examiner Van Nieuwenhuize, O
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03/82 (P4/C01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 30 9802

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.CI.7)
A	<p>"KAUTSCHUK VERARBEITEN MIT EXTRUDER + ZAHNRADPUMPE"</p> <p>PLASTVERARBEITER, ZECHNER UND HUETHIG VERLAG GMBH. SPEYER/RHEIN, DE, vol. 44, no. 1, 1993, pages 44-45, XP000362068</p> <p>ISSN: 0032-1338</p> <p>* page 44, right-hand column *</p>	11	
			TECHNICAL FIELDS SEARCHED (Int.CI.7)
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 8 October 2003	Examiner Van Nieuwenhuize, O
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03 82 (P4/C01)

ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.

EP 01 30 9802

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

08-10-2003

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
EP 0492425	A	01-07-1992	US	5156781 A	20-10-1992
			DE	69124788 D1	03-04-1997
			DE	69124788 T2	12-06-1997
			EP	0492425 A1	01-07-1992
			ES	2098308 T3	01-05-1997
			JP	3268804 B2	25-03-2002
			JP	5116200 A	14-05-1993
			US	5267847 A	07-12-1993
EP 0508080	A	14-10-1992	DE	4111217 C1	02-07-1992
			EP	0508080 A2	14-10-1992
			JP	5124086 A	21-05-1993
EP 0968814	A	05-01-2000	JP	2000079642 A	21-03-2000
			EP	0968814 A2	05-01-2000
			US	6372070 B1	16-04-2002
US 4171193	A	16-10-1979	DE	2700003 A1	06-07-1978
			AT	368946 B	25-11-1982
			AT	816277 A	15-04-1982
			FR	2375979 A1	28-07-1978
			GB	1581450 A	17-12-1980
US 5378415	A	03-01-1995	DE	4111219 A1	08-10-1992
			DE	59203516 D1	12-10-1995
			EP	0508079 A2	14-10-1992
			ES	2079708 T3	16-01-1996
			JP	5124087 A	21-05-1993
WO 9014939	A	13-12-1990	DE	3917523 A1	06-12-1990
			AT	107886 T	15-07-1994
			DE	9004535 U1	02-08-1990
			DE	59006305 D1	04-08-1994
			WO	9014939 A1	13-12-1990
			EP	0426790 A1	15-05-1991
			ES	2057556 T3	16-10-1994
			JP	3502186 T	23-05-1991
WO 8903754	A	05-05-1989	EP	0386068 A1	12-09-1990
			SE	8704203 A	08-02-1989
			WO	8903754 A1	05-05-1989
EP 0391003	A	10-10-1990	JP	2263609 A	26-10-1990
			JP	6041135 B	01-06-1994
			DE	68909588 D1	04-11-1993
			DE	68909588 T2	17-02-1994

EPO FORM P4450

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 30 9802

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

08-10-2003

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0391003, A		EP 0391003 A2	10-10-1990
EP 1084814 A	21-03-2001	EP 1084814 A1	21-03-2001
		JP 3330126 B2	30-09-2002
		JP 2001150515 A	05-06-2001
		US 6468067 B1	22-10-2002

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82